

Please Note: Tank sizes do not take into account restrictions created by heaters, anode and cathode bars and other factors. Therefore please treat this data as a guide only. Tank Name	Length cms	Length inches	Width cms	Width inches	Working Depth cms	Working Depth inches	Face Diagonal cms	Face Diagonal inches	Body Diagonal inches
Acid Etch of Steels	38	14.96	61	24.02	65	25.59	72	28.35	38.19
Chromic anodise	177	69.69	200	78.74	27	10.63	267	105.12	105.51
Chemical Film of Aluminium (Alocrom)	76	29.92	242	95.28	104	40.94	254	100	107.87
Aluminium Chemical Milling	451	177.56	126	49.61	184	72.44	468	184.25	197.64
Chemical Film of Aluminium (Alocrom)	87	34.25	186	73.23	154	60.63	205	80.71	100.79
Etch titanium to RPS 675 method A	30	11.81	186	73.23	154	60.63	188	74.02	95.67
Ammonium Nitrate Cadmium Strip	79	31.1	83	32.68	112	44.09	115	45.28	63.39
Anodic Strip	91	35.83	242	95.28	104	40.94	259	101.97	109.84
Black Dye	91	35.83	242	95.28	104	40.94	259	101.97	109.84
Blue Dye (Sanodal Blue G Dye)	67	26.38	66	25.98	74	29.13	94	37.01	47.24
Bright Tin Plating	75	29.53	75	29.53	75	29.53	106	41.73	51.18
Bronze Plating	214	84.25	88	34.65	85	33.46	231	90.94	96.85
Cadmium Plating Bright	203	79.92	83	32.68	112	44.09	219	86.22	96.85
Cadmium Plating Bright	113	44.49	82	32.28	108	42.52	140	55.12	69.69
Cadmium Plating LHE	113	44.49	82	32.28	108	42.52	140	55.12	69.69
Cadmium Plating Dull	244	96.06	91	35.83	106	41.73	260	102.36	110.63
Chrome Strip	112	44.09	83	32.68	112	44.09	139	54.72	70.47
Chromic Acid Anodising	90	35.43	305	120.08	100	39.37	318	125.2	131.1
Chromium Plating (Heef 25 solution)	180	70.87	83	32.68	117	46.06	198	77.95	90.55
Chromium Plating (Conventional)	172	67.72	83	32.68	117	46.06	191	75.2	88.19
Chromium Plating (Conventional)	203	79.92	83	32.68	117	46.06	219	86.22	97.64
Chromium Plating (Heef 25 solution)	300	118.11	73	28.74	75	29.53	308	121.26	124.8
Copper Plating	212	83.46	90	35.43	100	39.37	230	90.55	98.43
Dasic D53 Paint stripper		0		0		0	0	0	0
Electroless Nickel Plating	75	29.53	75	29.53	75	29.53	106	41.73	51.18
Enviralloy Ni 12-15 Zinc-Nickel Plating		0		0		0	0	0	0
Etch to MPS 180-031	79	31.1	29	11.42	70	27.56	84	33.07	42.91
Etch to WAPS 09-02	75	29.53	75	29.53	75	29.53	106	41.73	51.18
Etching to Titanium to RPS448	75	29.53	75	29.53	75	29.53	106	41.73	51.18
Fluorocarbon Seal for Hard Anodise (PTFE)	15	5.91	15	5.91	90	35.43	21	8.27	36.22
Hard Acid Anodise	91	35.83	242	95.28	104	40.94	259	101.97	109.84
Magnesium Chromate	75	29.53	75	29.53	75	29.53	106	41.73	51.18
Nickel Alloy Chemical Milling Solution	167	65.75	152	59.84	139	54.72	225	88.58	103.94
Nitric / Hydrofluorosilicic Acid Etch titanium to RPS 675 M2	30	11.81	186	73.23	154	60.63	188	74.02	95.67
Pure Gold Plating	75	29.53	75	29.53	75	29.53	106	41.73	51.18
Red Dye (Firey Red Dye ML)	67	26.38	66	25.98	74	29.13	94	37.01	47.24
Silver Plating to Def Stan 03-9	120	47.24	75	29.53	74	29.13	141	55.51	62.6
Stainless Steel Chemical Milling Solution	167	65.75	152	59.84	139	54.72	225	88.58	103.94
Stainless Steel Passivation to Def Stan 03-2 Method M Soln 1	72	28.35	36	14.17	52	20.47	80	31.5	37.4
Stainless Steel Passivation to Def Stan 03-2 Method M Soln 2	72	28.35	36	14.17	52	20.47	80	31.5	37.4
Stripping of chrome from aluminium		0		0		0	0	0	0
SULPHAMATE NICKEL PLATING TO DEF STAN 03-27	120	47.24	75	29.53	74	29.13	142	55.91	62.99
Sulphuric Acid Anodising	100	39.37	186	73.23	154	60.63	211	83.07	102.76
Sulphuric Acid Anodising	90	35.43	305	120.08	100	39.37	318	125.2	131.1
Sulphuric Acid Etching to RPS 674	75	29.53	725	285.43	240	94.49	728	286.61	301.57
Tin Plating (alkaline to Def Stan 03-08)		0		0		0	0	0	0
Tin Plating to (Acid Def Stan 03-8 Dull)	120	47.24	75	29.53	74	29.13	142	55.91	62.99
Titanium Chemical Milling Solution	167	65.75	152	59.84	139	54.72	225	88.58	103.94
White layer removal to RPS 278	75	29.53	75	29.53	75	29.53	106	41.73	51.18
Zinc Plating	150	59.06	75	29.53	74	29.13	168	66.14	72.44